

Microconcrete S

DESCRIPTION

Microconcrete S is a coarse 2 ingredient quartz cement mortar consisting of concrete, selected high – quality aggregates, inorganic pigments and artificial resins.

Origin: Satine Spain

Granulometry: 0~0.3 mm

Total thickness: 2.5 mm

Proposed layers: 2

Areas of application: Smooth concrete, Warm concrete (floor heating), Wood, Tiles-Marble, Glass, Plasterboard – Cement bonded fiberboard. Indoor – Outdoor spaces. Pool-Flooring/Wall

Application: With a stainless spatula

Waterproofing: Mild passability (2 layers of impregnation) / High passability (2 layers of crystallization with a 2 ingredient polyurethane crystallizer)

Compression strength (7 days): 70N / mm²

Compression strength (28 days >): 95N / mm²

Tensile strength (28 days): 12N / mm²

Adhesion on concrete (28 days): 1,75 N / mm²

Application thickness: 1mm/layer

Package: 22 kg bucket + resin 7.2 lt

Colorings: 40 standard colors and all NCS-RAL colors on demand

Texture – Appearance: Slightly porous surface with a the slightest of color variations